

CEMENT CONCRETE ROLLED CURB

NOTES:

- 1. CONTRACTION JOINTS OF ONE OF THESE TYPES SHOWN ABOVE TO BE PLACED 10' C/C. COMPLETELY SEVER THE STRUCTURE TO THE POINTS SHOWN. JOINTS MAY BE MADE BY INSERTING MIN. $\frac{1}{16}$ " BITUMINOUS FILLER DUMMY JOINTS. JOINTS SHALL BE CLEANED AND EDGED.
- 2. CONCRETE SHALL BE CEMENT CONCRETE CLASS "C".
- 3. FINISHED WORK SHALL NOT VARY MORE THAN %" IN GRADE AND 14" IN ALIGNMENT WHEN CHECKED WITH 10' STRAIGHT EDGE.
- 4. EXPOSED SURFACES SHALL BE BRUSHED WITH A FIBER HAIR BRUSH.
- 5. WHITE PIGMENTED OR TRANSPARENT CURING COMPOUND SHALL BE APPLIED AS OUTLINED IN THE STANDARD SPECIFICATIONS.
- 6. FURTHER REQUIREMENTS SHALL BE AS SPECIFIED IN THE STANDARD SPECIFICATIONS.
- 7. ROLLED CURB SHALL ONLY BE USED WITH A 6" THICK SIDEWALK SECTION.

APPROVED

| City Engineer | CITY OF BELLINGHAM | DRAWING |
|-6-08 | ROLLED CURB AND GUTTER | CG-204